

DATA SHEET

AGM Deep Cycle 12 -Volt



Application: Wherever Sealed, Leak Proof, Deep Cycle 12-volt batteries are needed.

> Dimensions: 12.87" (327mm)L 7.09" (180mm)W 10.79" (274mm)H

Type: Sealed Non-Spillable Lead Acid (AGM)

Case material: ABS / Heat Sealed

US AGM 12V150 SPECIFICATIONS																				
BCI												Standard	AMP	MINUTES	MINUTES	MINUTES				Wet
Group	Model	1-hr	2-hr	5-hr	6-hr	10-hr	20-hr	48-hr	72-hr	100-hr	Voltage	Terminal	HOURS	@	@	@	Length	Width	Height	Weight
Size		Rate	Rate	Rate	Rate	Rate	Rate	Rate	Rate	Rate		Туре	(20 HR. RATE)	75 AMPS	56 AMPS	25 AMPS	12.87"	7.09"	10.79"	Lbs (kg)
GC12	US AGM 12V150	106	117	133	137	142	150	159	163	166	12	T11	150	90	120	323	(327)	(180)	(274)	93(42.2)

CHARGING INSTRUCTIONS:

15 Nominal Charge Current (amps) 30 Max Charge Current (w/ temp. compensation) 14.9 Max Charge Voltage (temp. compensated) 13.8 Float/Maintenance Voltage (temp. compensated) -4 mV/cell/°C (-2 mV/cell/°F)


Temperature Compensation

For automatic chargers, use settings compatible with AGM batteries

Do not charge at temperature corrected voltages above 15 volts (2.5 volts/cell). Use of a voltage controlled charger is a requirement for warranty coverage. For best cycle life, limit discharge to less than 50% of the battery's 20 hour capacity.

Deep cycle batteries need to be equalized periodically. Equalizing is an extended, low current charge performed after the normal charge cycle. This extra charge helps keep all cells in balance. Actively used batteries should be equalized once per month. Manually timed chargers should have the charge time extended approximately 3 hours. Automatically controlled chargers should be unplugged and reconnected after completing a charge.


All of our sealed AGM batteries are specifically manufactured for U.S. Battery under our guidelines assuring our customers they are being provided the highest quality AGM batteries available.



US AGM 12V150


DATA SHEET


AGM Deep Cycle 12 -Volt







T11









U.S. Battery Operating Temperature Guidelines

For charging, we recommend staying within 0°F to 120°F (-18 to 49°C) to avoid charging frozen batteries at low temperature or going into

thermal runaway at high temperature.

For discharging, we recommend -20°F to 120°F (-29 to 49°C).

Batteries discharged at temperatures below 32°F (0°C) should be recharged immediately to avoid freezing.

Batteries discharged at temperatures above $120^{\circ}F$ ($49^{\circ}C$) should be allowed to cool before recharging.

Extreme temperatures can substantially affect battery performance and charging. Cold reduces battery capacity and retards charging. Heat increases water usage and can result in overcharging. Very high temperatures can cause "thermal run-away" which may lead to an explosion or fire. If extreme temperature is an unavoidable part of an application, consult a battery/charger specialist about ways to deal with the problem.

Data references within this publication are nominal and should not be considered or construed as maximum or minimum values for specifications or for final design. Data for this product type and model may vary from what is shown in this publication, and U.S. Battery Mfg, Co. makes No warranties, expressed or implied based on the data within this publication.

©2021 U.S. Battery Mfg., Co. All rights reserved. U.S Battery is not liable for damages that may occur from any information provided in or omitted from this publication, under any circumstances. U.S. Battery Mfg., Co. reserves the right to make changes or adjustments to this publication at any time without notices or obligations.



1675 Sampson Avenue Corona, CA 92879 (800) 695-0945 1895 Tobacco Road Augusta, GA 30906 (800) 522-0945 717 North Belair Rd. Evans, GA 30809 (888) 811-0945